PRB JOINT XT



WATERPROOF GROUT FOR WIDE JOINTS - THICK AND FLUID CONSISTENCY

The 🛟 s of PRB JOINT XT

- Fluid consistency for floors, Thick consistency for walls and floors
- For joints from 3 to 15 mm
- Easy to apply and to clean
- Smooth, clean finish





PACKAGING

- Paper bag containing 25 kg.
 Plastic bag containing 5 kg (JOINT LARGE CARRELAGE).

STORAGE LIFE: 12 months.

CONSUMPTION/USE

Consumption varies according to tile size, as well as the depth and width of the joints: from 200 to 800 g/m² when laying standard tiles.

To calculate the amount needed:

- refer to the consumption table.
- use our calculator tool at: www.prb.fr

COLOUR: available in 15 different colours (25 kg), 4 different colours (5 kg).

Class CG2 WA

AREA OF USE

USES

- Walls & floors
- Interior & exterior New and renovation work.
- · All types of ceramic tiles or similar.
- Technical Specifications and French DTU Standards for glued or grouted applications.

COMPATIBLE COVERINGS

- Glazed or porcelain stoneware.Extruded stoneware.
- Terracotta*.
- "Pâte de verre" mosaics.
- Natural stone (limestone, marble or
- Cement and reconstituted stone slabs*.
- For terracotta, natural stone and cement or stone slabs, we recommend that you carry out a stain test before use.

LIMITS OF USE

Do not apply to/in:

- · Areas subject to high-pressure cleaning or aggressive products. Wooden panels.
- Areas in contact with seawater, thermal spring water and other aggressive waters (in this case, we recommend using PRB COL & JOINT ÉPOXY).
- · Earthenware tiles (in this case we recommend using PRB JOINT FIN, as it is non-abrasive).
- In areas subject to specific hygiene regulations, this product must be used in accordance with the guidelines set out in the special technical specifications, trade rules and/or health and safety regulations.

APPLICATION CONDITIONS

- Between 5 and 30° C.
- Do not apply to frozen, thawing, hot or damp surfaces. Do not apply to surfaces in full sunlight or during heavy rain and strong winds.

TECHNICAL CHARACTERISTICS

INGREDIENTS

- Fluid binders
- · Fine quartz-based mineral fillers.
- · Water-retention agents & setting agents.
- · Plasticisers.
- UV-resistant mineral pigments.
- · Water-repellent agents.

PRODUCT

POWDER:

- Grain size: <800 µm
- PASTE:
- Density: 1.95 ± 0.1

• pH (alkaline): 12.5 ± 0.5 **AVERAGE PERFORMANCE WHEN** HARDENED:

- Class according to EN 13888: CG2 WA.
- Modulus of elasticity: $15,000 \pm 5,000$ MPa
- Compressive strength: ≥ 20 MPa
- Reaction to fire (non-combustible): A1 (M0)
 Hardness (Shore D): 80

APPLICATION

- 2 mixing consistencies:
- . thick consistency (walls and floors): 19 to 21%
- fluid consistency (floors): 21 to 23%
- Mixing time: 3 to 5 mins.Manipulation time (workable life): 60 to 90 mins
- . Setting time: 3 to 5 hrs
- . Can be walked on after (light circulation): 12 hrs
- Can be walked on after: 24 hrs
- Minimum joint width: 3 mm
- Maximum joint width: 15 mm

NB: These values are estimates based on laboratory or on-site testing. The conditions of use, the type of material used and its level of wear and tear can significantly alter these

UTILISATION

Please refer to the PRB Process Sheets

PREPARATION

Before applying, make sure that:

- . The tile adhesive has completely set or
- . The joints are clean, free of foreign matter, of even depth and free of excessive adhesive build-up
- Unglazed or porous tiles should be moistened before use or treated with a suitable tile protecting agent.

PRODUCT PREPARATION

Mix PRB JOINT XT to the desired consistency:

- Thick consistency (floors and walls): with 4.75 to 5.25 litres of clean water per
- Fluid consistency (floors): with 5.25 to 5.75 litres of clean water per 25 kg bag.

- Mix with an electric mixer at low speed until you obtain a smooth, lump-free paste.
- . Do not re-mix or add water when the mortar begins to stiffen (when it is beginning to set) and be sure to respect the manipulation time (workable life of the mix).
- . The quantity of water and mixing time must be kept constant in order to ensure: an even colour from one mix to the next, optimum hardness & finish.
- Make sure that mortar from the same batch is used for each job (tile or set of

APPLICATION

USING A SCRAPER, FLOAT OR GROUTING

 Press PRB JOINT XT into the joints, using alternating strokes diagonally across the joints, pressing firmly so that the joint is properly filled without gaps.

FINISHING & CLEANING

POWDER-COATED FINISH:

For floors, the fresh joint can be finished with a powder coating so that it can be sealed by hand or with a machine.* This increases the surface hardness of the joint and ensures that the joint is flush with the surface of the tiles

(* We recommend you carry out a test beforehand, depending on the machine and the type of tiles.)

• After filling the joints, lightly dust with PRB

JOINT XTPOWDER.

- Rub diagonally using a scraper.
- · Seal with a cloth and sweep up any excess.
- . Depending on the type of covering (porous, uneven, etc.), any traces of grout on the surface of the tiles should be removed with a cloth or sponge before the grout sets

SPONGE FINISH:

- Once firm, clean the tiles with a fine foam sponge or sponge float, diagonally across the joints, rinsing frequently, and taking care not to hollow out the joints
- . Do not let it harden on the tiles.
- When the joint has hardened, finish cleaning with a dry cloth.

We recommend using a coarse sponge to remove excess mortar and a fine sponge for finishing. The aesthetic and mechanical requirements of the joint can be met by using specialist equipment.

PRECAUTIONS FOR USE

- · Contains cement and/or lime.
- · Please read the packaging safety label and safety data sheet before use.

Technical Data Sheet - 20 January 2025